



ARDEX BR 460 FLOW

High Performance, Flowable, Structural Micro Concrete

Shrinkage compensated

Excellent flow and levelling properties

Excellent adhesion to concrete

Contains active corrosion inhibitor

Low resistivity (<15,000Ω cm)

Used in conjunction with ARDEX BRX 60 LO Low Output Anodes

High early & final strength

Low odour



ARDEX Australia Pty Ltd

20 Powers Road
Seven Hills NSW 2147
1300 788 780
technicalservices@ardexaustralia.com
www.ardexaustralia.com

ARDEX New Zealand Ltd

15 Alfred Street
Onehunga, Auckland 1061
Phone: 0800 227 339
Email: info@ardexnz.com
Internet: www.ardex.co.nz

ARDEX BR 460 FLOW

High Performance, Flowable, Structural Micro Concrete

DESCRIPTION

ARDEX BR 460 FLOW High Performance, Flowable Structural Micro Concrete is a pourable repair mortar designed for reinstating horizontal concrete surfaces damaged through concrete spalling and other chemical or mechanical causes. ARDEX BR 460 FLOW exhibits superior flow characteristics and is capable of being applied in thicknesses of 20mm to 200mm in one pour. It is designed to be used in conjunction with ARDEX BRX 60 LO Low Output Anodes for ultimate corrosion control and cathodic prevention.

PREPARATION

The substrate must be clean, sound and free from all grease, oil, dust and other surface contaminants such as curing membranes. Damaged or contaminated concrete must be removed to obtain a good bond to the substrate. Cut the edges of the repair vertically to a minimum depth of 20mm. All surface laitance must be removed. Exposed reinforcing steel should be cleaned to remove all residual rust and concrete residue. In accordance to best practice, as outlined in the ACRA Guide to Concrete Repair and Protection Concrete HB84-2006 Chapter 6, concrete should be removed from around and behind all corroding rebar to avoid future contamination of the repaired area. Exposed reinforcing must be cleaned and protected with BR 10 ZP Zinc-rich Primer in a continuous film. If ARDEX BRX 60 LO Low Output Anodes are used, please refer to respective Technical Datasheet for Surface Preparation and rebar priming methods.

PRIMING

The prepared substrate should be pre-soaked for 24 hours but at least 2 hours before applying ARDEX BR 460 FLOW to reduce the porosity of the substrate. Remove excess freestanding water on the surface prior to the application of BR 460 FLOW. The surface should be mat damp but without standing water.

Priming for reinforcement steel

Use BR 10 ZP Zinc-rich Primer as primer for steel reinforcement in concrete. Apply BR 10 ZP in a continuous film; apply a second coat if needed. ARDEX BR 10 ZP should be cured prior to pouring the micro concrete. If ARDEX BRX 60 LO Low Output Anodes are used, please refer to respective Technical Datasheet for Surface Preparation and rebar priming methods.

FORMWORK PREPARATION

The area to be poured must be enclosed with good quality rigid watertight formwork. The formwork must be able to rigidly confine the ARDEX BR 460 FLOW until it has set. It is recommended to use an appropriate form release agent. Formwork should be flushed out just prior to application without any standing water present.

MIXING

Use approximately 2.4 – 2.7L water per 20kg bag of ARDEX BR 460 FLOW. Measure the appropriate amount of water into a clean suitable sized pail and then add the entire contents of the bag while mixing with a heavy duty electric drill and ARDEX Mixing Paddle on slow-medium speed (approx. 400-600 rpm). Once all of the powder has been added, mix for approximately 2 to 3 minutes to fully homogenise. The mixed material should be poured immediately for best results.

APPLICATION

ARDEX BR 460 FLOW is to be applied onto the pre-wetted substrate. Make sure that the micro concrete is applied whilst the substrate is still wet. It should be applied in a continuous pour to avoid cold joints. It is recommended to smooth the material after each pour with a steel trowel.

CURING

As with all cementitious products ARDEX BR 460 FLOW must be cured properly to ensure maximum performance. It is recommended to apply an approved curing compound after final set on all exposed areas. If formwork is used, the curing compound should be applied immediately after the formwork is removed. Curing compounds should be applied onto the surface of the ARDEX BR 460 FLOW according to the Technical Datasheet of the curing compound. If the surface of ARDEX BR 460 FLOW was not restrained during the cure, any laitance should be removed (generally can be rinsed off) before applying the curing compound.

SET TIMES

Pot Life: to be used in a continuous pour immediately after mixing
Initial Set: 5 – 8 hours
Final Set: 6 – 9 hours

ARDEX BR 460 FLOW

High Performance, Flowable, Structural Micro Concrete

PACKAGING

ARDEX BR 460 FLOW is packed in polylined paper sacks – net weight 20kg.

COVERAGE

20kg of powder makes approximately 10 litres of mortar.

At 20mm thickness: 0.5m²

At 100mm thickness: 0.1m²

SHELF LIFE

ARDEX BR 460 FLOW has a shelf life of 12 months when stored in the original, unopened packaging in a dry place at 23°C and 50% relative humidity.

CLEAN UP

Clean all tools in water immediately after use.

Pay Attention to the following:

Do not over-water. Long narrow repairs should be avoided where possible and pours arranged to achieve a length: minimum thickness ratio, of not more than 20:1.

SAFETY DATA

This product may cause irritation and an allergic reaction to the skin. It may cause serious eye injury and irritation to the respiratory system. In case of contact with the eyes rinse with running water until advised to stop by the Poisons Information Centre or a doctor, or for at least 15 minutes. Wear protective gloves, clothing, eye and face protection. Avoid inhaling dust/fumes/gas/mist/vapours/spray. Ensure adequate ventilation during mixing and application. Store locked up. Check with your local Council regarding the disposal of contents, dispose of packaging thoughtfully and recycle where possible. Keep out of the reach of children. Call the Poisons Information Centre on 131 126 (AUS) and 0800 764 766 (NZ) or call a doctor if you feel unwell. Additional information is in the Safety Data Sheet (SDS) at www.ardexaustralia.com

TECHNICAL DATA

Water	2.4 - 2.7l/20kg
Wet density	~2.30g/cc
pot life @23°C	To be used in a continuous pour immediately after mixing
Initial Set	5 - 8h
Final Set	6 - 9h
Flow AS 1478.2-2005	300mm - 650mm (depending on water ratio)

EN 1504-3 R4 TESTING DATA

	Test Method	R4 Requirements	Typical Results
Compressive Strength	EN 12190	≥ 45MPa	1d >10MPa 7d >35MPa 28d 45-70MPa
Chloride Ion Content	EN 1015-17:2000	≤ 0.05%	0.002%
Adhesive Bond	EN 1542	≥ 2.0MPa	≥ 2.0MPa
Shrinkage and Expansion	EN 12617-4	≥ 2.0MPa	≥ 2.0MPa
Carbonation Resistance	EN 13295:2004	d ≤control concrete	pass(MC0.45)
Elastic Modulus	AS 1012.17*	≥ 20GPa	27.4GPa
Coefficient of Thermal Expansion	AASHTO T336-11 **	declared value	13.9ms/°C
Capillary Absorption	EN 13057:2002	≤ 0.5kg/(m ² Xh ^{0.5})	0.08kg/(m ² Xh ^{0.5})

ADDITIONAL TECHNICAL DATA

	Test Method	Typical Results
Flexural Strength	EN 12190	28d 8-11MPa
Drying Shrinkage 23°C 50% RH	AS 1478.2-2005	7d <400ms 28d <700ms
Bulk Resistivity	internal method	7d <6000 Ω.cm 28d <10,000 Ω.cm 56d <11,000 Ω.cm

*AS1012.17 done in place of EN 13412

**AASHTO T336-11 done in place of EN1770

ms = micro strains

GUARANTEE

ARDEX Australia Pty Ltd ("we" or "us") guarantees this product ("our goods") is free from manufacturing defects and will perform to any applicable specification published by us for 10 years from the date of purchase. Our liability under this guarantee is limited at our option to replacement of the product, repair of any damage to the immediate surface or area of application of the product, or compensation, in each case if we are satisfied loss or damage was due to a breach of this guarantee. This guarantee does not apply if damage or loss is due to failure to follow published instructions or any act or circumstance beyond our control, including shade variations and efflorescence. If you wish to make a claim under this guarantee you must notify us (ARDEX Australia Pty Ltd, 20 Powers Road Seven Hills NSW 2147; Toll Free: 1800 224 070; Email: technicalservices@ardexaustralia.com) and provide evidence of your purchase of the product within 30 days of any alleged loss or damage occurring. We reserve the right to ask you for satisfactory evidence of any alleged loss or damage. Any claim under this guarantee is at your cost. This guarantee is in addition to any rights or remedies you may have as a "consumer" under the Australian Consumer Law and to that extent you need to be aware that: "Our goods come with guarantees that cannot be excluded under the Australian Consumer Law. You are entitled to a replacement or refund for a major failure and for compensation for any other reasonably foreseeable loss of damage. You are also entitled to have the goods repaired or replaced if the goods fail to be of acceptable quality and the failure does not amount to a major failure".

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standards. Our instructions and recommendations are only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may affect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2019.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.

This datasheet was issued in October 2019 and is valid for 3 years, in some instances a newer version may be published. Always refer to www.ardexaustralia.com for the latest technical data from ARDEX Australia Pty Ltd.