



ARDEX HYDROSTOP WPM 1950

Polymeric Hydrophilic Swellable Rubber Joints

Non-greasy, non-sticky, odourless and non-toxic

Excellent for applications to rough concrete surfaces

No premature expansion; allows concrete to gain strength before expansion

Easy to install by bonding, nailing or casting into joint faces with the aid of ARDEX CA 20P

Solves detailing problems in construction

Excellent performance - Swelling properties unaffected by long term cyclic wetting and drying; limited loss of integrity of waterstop

Sustains effective seal in wet conditions

ARDEX Australia Pty Ltd
20 Powers Road
Seven Hills NSW 2147
1300 788 780
techinfo@ardexaustralia.com
www.ardexaustralia.com

ARDEX New Zealand Ltd
15 Alfred Street
Onehunga, New Zealand
0800 227 339
info@ardexnz.com
www.ardex.co.nz

ARDEX Hydrostop WPM 1950

Polymeric Hydrophilic Swellable Rubber Joints

PRODUCT DESCRIPTION

Due to its particular chemical composition, ARDEX Hydrostop WPM 1950 hydrophilic rubber joint remains unaltered over time even at maximum expansion. It is dimensionally stable even after numerous hydration and de-hydration cycles while maintaining its ability to increase its volume.

In its maximum expansion, in all its sections, ARDEX Hydrostop WPM 1950 hydrophilic rubber joint is mechanically strong and elastic. The swelling process is controlled and designed to be compatible with fresh concrete.

COMPOSITION

ARDEX Hydrostop WPM 1950 is made up of rubber and aggregated polypropylene with high cohesion polymeric binders. These hydrophilic components activate in wet conditions which allows the Hydrostop to increase in volume.

APPLICATION INSTRUCTIONS

ARDEX Hydrostop WPM 1950 must be applied to the support by nailing or casting into joint faces with the aid of ARDEX CA 20 P, ARDEX WA 98 Solvent Based Contact Adhesive, double-sided adhesive tape, or cement adhesives to remain attached in the early stages of concrete casting. For maximum performance ARDEX Hydrostop WPM 1950 should be placed between the reinforcing bars or in a support with raised edge of at least 8-10cm. The joints are realized by matching sideways the rubber strip for at least 5cm, while avoiding overlapping.

The application surface should be clean, compact, properly vibrated and free of any irregularities.

BENEFITS

ARDEX Hydrostop WPM 1950 is non-greasy, non-sticky, odourless and non-toxic. Once the Hydrostop is secured into place, no additional bonding is required and it will maintaining its seal in vertical laying as well as wet conditions.

PACKAGING

ARDEX Hydrostop WPM 1950 is packed in cartons with 6 rolls of 8m long coils giving a total of 48 linear meters per carton.

Dimensions:

20mm x 10mm x 8m roll

6 rolls per carton; 48 linear metres per box.

Technical Data

Specific gravity	ISO 1183	1.26kg/L
Operating temperature	ISO 458/2	>+4°C
Max. expansion		350%
Hardness	ISO 868	60 shore A
Load at break	ISO 527	25 MPa
Elongation at break	ISO 527	300%
Durability		unlimited

DISCLAIMER

The technical details, recommendations and other information contained in this data sheet are given in good faith and represent the best of our knowledge and experience at the time of printing. It is your responsibility to ensure that our products are used and handled correctly and in accordance with any applicable Australian Standard, our instructions and recommendations and only for the uses they are intended. We also reserve the right to update information without prior notice to you to reflect our ongoing research and development program. Country specific recommendations, depending on local standards, codes of practice, building regulations or industry guidelines, may effect specific installation recommendations. The supply of our products and services is also subject to certain terms, warranties and exclusions, which may have already been disclosed to you in prior dealings or are otherwise available to you on request. You should make yourself familiar with them.

© ARDEX Australia Pty Ltd 2018.

All aforementioned products are the trade marks of ARDEX Australia Pty Ltd, its licensors and affiliates.

ARDEX Australia Pty Ltd
1300 788 780

Toll Free Technical Services:
1800 224 070 (Australia)

ARDEX New Zealand Ltd
0800 227 339

June 2018